

报告编号(No.): AB22020275

第 1 页共 4 页

委托方
Applicant 探路者控股集团股份有限公司

生产方
Manufacture 福建省宏港纺织科技有限公司

客户认定
样品信息
Submitted Sample Description
商标: 探路者
样品名称: 针织面料,
数量: 1,
描述: 21SS 香水紫-F220902165 浅紫色针织物
产品等级: 合格品,
安全类别: B 类
声明款号: QAMMAL84327/QAZZAL84113
面料编号: FK07280/G21SS3660;

检验类型 Test Type	委托检验	来样日期 Date Received	2022-09-21	签发时间 Date Issued	2022-09-26
-------------------	------	-----------------------	------------	---------------------	------------

判定依据 Performance Standard	GB 18401-2010 国家纺织产品基本安全技术规范 Q/CPTLZ 0014.2-2020 TIEF SKIN 功能性纺织品材料 X2 Q/CPTLZ 0014.7-2017 TIEF COOL 功能性纺织品材料 T/FM 002-2020 针织面料理化性能要求
------------------------------	---



批准 Approved by

Wang Baojun (Director)



备注
Notes

委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.
除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer.
*暂未申请认可。*The test isn't requested for confirmation temporarily.

报告编号(No.): AB22020275



第 2 页共 4 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
纤维含量 (%) FZ/T 01057-2007、GB/T 38015-2019			符合
	锦纶 88	锦纶 87.5	
	氨纶 12	氨纶 12.5	
pH 值 GB/T 7573-2009			符合
	4.0~8.5	6.5	
pH 值萃取介质为氯化钾溶液。			
甲醛含量 (mg/kg) GB/T 2912.1-2009			符合
	≤75	未检出	
本方法的测定低限为 20mg/kg, 低于测定低限结果为“未检出”。			
异味 GB 18401-2010 条款 6.7			符合
	无	无异味	
可分解致癌芳香胺染料 (mg/kg) GB/T 17592-2011			符合
	≤20	未检出	
本方法的检出限为 5mg/kg, 低于检出限的结果为“未检出”。			
耐水色牢度 (级) GB/T 5713-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐酸汗渍色牢度 (级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐碱汗渍色牢度 (级) GB/T 3922-2013			符合
变色	≥3-4	4-5	



报告编号(No.): AB22020275



第 3 页共 4 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐干摩擦色牢度(级) GB/T 3920-2008			符合
沾色	≥3-4	4-5	
耐湿摩擦色牢度(级) GB/T 3920-2008			符合
沾色	≥3	4-5	
耐皂洗色牢度(级) GB/T 3921-2008			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
A(1): 温度 40℃, 时间 30min, 钢球 0 颗			
耐光色牢度(级) GB/T 8427-2019 方法 3			符合
变色(浅色)	≥3	>3	
一阶段/对于深浅条的面料, 按蓝色羊毛标样 4 级进行曝晒, 深色按蓝色羊毛标样 4 级评级, 浅色按蓝色羊毛标 3 级评级。			
耐光、汗复合色牢度(碱汗)(级) GB/T 14576-2009			符合
变色	≥3-4	4-5	
起球(级) GB/T 4802.1-2008			符合
	≥3-4	4-5	
方法 E: 压力 780cN, 起毛 0 次, 起球 600 次/具有特殊结构的织物加测反面			
防紫外线性能 GB/T 18830-2009			符合
UVA 平均透射比(%)	<5	2.21	
UPF 紫外线防护系数	>50	124	
透湿率(g/(m ² ·24h)) GB/T 12704.1-2009			符合
	≥2200	11530	

报告编号(No.): AB22020275



第 4 页共 4 页

	标准 (称) 值 Requirement	实测值 Results	单项判定 Judgement
a) 温度 (38±2) °C, 相对湿度 (90±2) %			
接触瞬间凉感系数 Qmax (洗前) (J/(cm²·s))	*Q/CPTLZ 0014.7-2017 附录 A ≥0.15	0.25	符合
接触瞬间凉感系数 Qmax (洗后) (J/(cm²·s))	*Q/CPTLZ 0014.7-2017 附录 A ≥0.15	0.26	符合
干燥程序: 悬挂晾干, 洗涤程序: 4N×5			

以下空白

