

报告编号(No.): AB22004928

第 1 页共 3 页

委托方
Applicant 探路者控股集团股份有限公司

生产方
Manufacture 福建省宏港纺织科技有限公司

客户认定
样品信息
Submitted Sample
Description

商标: 探路者
样品名称: 针织布,
数量: 1,
描述: 19SS 黑色-F220228171 黑色针织物
产品等级: 合格品,
安全类别: B 类
声明款号:
TAJJBK92750/TAJJBK91749/TACCAK92226/TAJJAK92232/TAJJAK91231/QAMMAK94314
面料编号: FK07310

检验类型
Test Type

委托检验

来样日期
Date Received

2022-03-16

签发时间
Date Issued

2022-03-18

判定依据
Performance
Standard

FZ/T 73020-2019 针织休闲服装
GB 18401-2010 国家纺织产品基本安全技术规范
T/FM 002-2020 针织面料理化性能要求



批准 Approved by

Wang Baojun (Director)

(检验检测专用章)
Stamp

备注
Notes

委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.
除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer.
*暂未申请认可。*The test isn't requested for confirmation temporarily.

报告编号(No.): AB22004928



第 2 页共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
纤维含量(%) FZ/T 01057-2007 GB/T 38015-2019			符合
	锦纶 73	锦纶 74.2	
	氨纶 27	氨纶 25.8	
pH 值 GB/T 7573-2009			符合
	4.0~8.5	5.6	
pH 值萃取介质为氯化钾溶液。			
甲醛含量(mg/kg) GB/T 2912.1-2009			符合
	≤75	未检出	
甲醛含量的检出限为 20mg/kg, 低于检出限结果为“未检出”。			
可分解致癌芳香胺染料(mg/kg) GB/T 17592-2011 GB/T 23344-2009			符合
	≤20	未检出	
可分解芳香胺染料的检出限为 5mg/kg, 低于检出限的结果为“未检出”。			
异味 GB 18401-2010 条款 6.7			符合
	无	无异味	
耐水色牢度(级) GB/T 5713-2013			符合
变色	≥3-4	4-5	
沾色			
羊毛	≥3-4	4-5	
腈纶	≥3-4	4-5	
涤纶	≥3-4	4-5	
锦纶	≥3-4	4-5	
棉	≥3-4	4-5	
聚酯	≥3-4	4-5	
耐汗渍色牢度(级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			
羊毛	≥3-4	4-5	
腈纶	≥3-4	4-5	
涤纶	≥3-4	4-5	
锦纶	≥3-4	4-5	
棉	≥3-4	4-5	
聚酯	≥3-4	4-5	
耐干摩擦色牢度(级) GB/T 3920-2008			符合
	≥3-4	4-5	

报告编号(No.): AB22004928



第 3 页共 3 页

	标准 (称) 值 Requirement	实测值 Results	单项判定 Judgement
耐湿摩擦色牢度(级) GB/T 3920-2008			符合
	≥2-3	4-5	
耐皂洗色牢度(级) GB/T 3921-2008 A(1)			符合
变色	≥3-4	4-5	
沾色			
棉	≥3-4	4-5	
羊毛	≥3-4	4-5	
腈纶	≥3-4	4-5	
涤纶	≥3-4	4-5	
锦纶	≥3-4	4	
醋酯	≥3-4	4-5	
耐光色牢度(级) GB/T 8427-2008 方法 3			符合
	≥4	>4	
一阶段			
起毛起球(级) GB/T 4802.1-2008			符合
	≥3-4	4	
参数 E: 压力 780cN, 起球次数: 600 次			
洗液沾色程度(级) FZ/T 73020-2019 条款 6.1.11			符合
	≥3	4	

以下空白