

报告编号(No.): AB22026829

第 1 页 共 3 页

委托方
Applicant 探路者控股集团股份有限公司

生产方
Manufacture 上海汇良纺织材料有限公司

客户认定
样品信息
Submitted Sample Description
商标: 探路者
样品名称: 针织贴合布,
数量: 1,
描述: 藏蓝色复合针织物,
产品等级: 合格品,
安全类别: B 类
声明款号: QAMMFK93125/94126
面料编号: FW11010;

检验类型 Test Type	委托检验	来样日期 Date Received	2022-12-06	签发时间 Date Issued	2022-12-19
-------------------	------	-----------------------	------------	---------------------	------------

判定依据 Performance Standard	FZ/T 73045-2013 针织儿童服装 GB 31701-2015 婴幼儿及儿童纺织产品安全技术规范 T/FM 002-2020 针织面料理化性能要求
------------------------------	--



批准 Approved by

Wang Baojun (Director)



备注
Notes

委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.
除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer.
*暂未申请认可。*The test isn't requested for confirmation temporarily.

报告编号(No.): AB22026829



第 2 页 共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
纤维含量(%) FZ/T 01057-2007、GB/T 2910.24-2009			符合
	面: 聚酯纤维 100 底: 聚酯纤维 100	面层: 聚酯纤维 100 底层: 聚酯纤维 100 胶除外	
分包项目, 分包机构为深圳中纺标			
pH 值 GB/T 7573-2009	4.0~8.5	6.3	符合
pH 值萃取介质为氯化钾溶液。			
甲醛含量(mg/kg) GB/T 2912.1-2009	≤75	未检出	符合
本方法的测定低限为 20mg/kg, 低于测定低限结果为“未检出”。			
异味 GB 18401-2010 条款 6.7	无	无异味	符合
可分解致癌芳香胺染料(mg/kg) GB/T 17592-2011	≤20	未检出	符合
本方法的检出限为 5mg/kg, 低于检出限的结果为“未检出”。			
耐水色牢度(级) GB/T 5713-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐酸汗渍色牢度(级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐碱汗渍色牢度(级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	



报告编号(No.): AB22026829



第 3 页 共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐干摩擦色牢度(级) GB/T 3920-2008			符合
沾色	≥3-4	4-5	
耐湿摩擦色牢度(级) GB/T 3920-2008			符合
沾色	≥2-3	4-5	
耐皂洗色牢度(级) GB/T 3921-2008			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
A(1): 温度 40℃, 时间 30min, 钢球 0 颗			
耐光色牢度(级) GB/T 8427-2019 方法 3			符合
变色(深色)	≥4	>4	
一阶段/对于深浅条的面料, 按蓝色羊毛标样 4 级进行曝晒, 深色按蓝色羊毛标样 4 级评级, 浅色按蓝色羊毛标 3 级评级。			
耐光、汗复合色牢度(碱汗)(级) GB/T 14576-2009			符合
变色	≥3-4	4-5	
洗液沾色程度(级) FZ/T 73020-2019 条款 6.1.11			符合
	≥3	4	
起球(级) GB/T 4802.1-2008			符合
	≥3-4	4-5	
方法 E: 压力 780cN, 起毛 0 次, 起球 600 次/具有特殊结构的织物加测反面			

以下空白

