

报告编号(No.): GA23000831-1

第 1 页 共 3 页

委托方  
Applicant 探路者控股集团股份有限公司

生产方  
Manufacture 际华三五四三针织服饰有限公司

客户认定  
样品信息  
Submitted Sample  
Description

商标: 探路者  
样品名称: 针织面料,  
数量: 1,  
描述: 黑色针织物, 色号: —  
产品等级: 合格品,  
安全类别: B 类  
声明款号: QAJJAL93208、 QAMMAL93226、 QAMMAL94107、 TAJJAL92404、 TAJJBL91742、  
TAJJBL92743  
面料编号: FK08050;

检验类型 Test Type	委托检验	来样日期 Date Received	2023-04-19	签发时间 Date Issued	2023-04-24
-------------------	------	-----------------------	------------	---------------------	------------

判定依据  
Performance  
Standard

FZ/T 73045-2013 针织儿童服装  
GB 31701-2015 婴幼儿及儿童纺织产品安全技术规范  
Q/CPTLZ 0014.4-2021 TIEF WARM 功能性材料 X3  
T/FM 002-2020 针织面料理化性能要求



批准 Approved by

Wang Baojun (Director)



委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.  
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning  
the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the  
report.

备注  
Notes

除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered  
on the results and conformity assessment in the report unless required by the customer.

\*暂未申请认可。\*The test isn't requested for confirmation temporarily.

样品及数据采用 AC23003801-1

报告编号(No.): GA23000831-1



第 2 页 共 3 页

标准 (称) 值 Requirement	实测值 Results	单项判定 Judgement
纤维含量 (%) FZ/T 01057-2007、GB/T 38015-2019		符合
锦纶 75	锦纶 76.6	
氨纶 25	氨纶 23.4	
pH 值 GB/T 7573-2009		符合
4.0~8.5	6.9	
pH 值萃取介质为氯化钾溶液。		
甲醛含量 (mg/kg) GB/T 2912.1-2009		符合
≤75	未检出	
本方法的测定低限为 20mg/kg, 低于测定低限结果为“未检出”。		
异味 GB 18401-2010 条款 6.7		符合
无	无异味	
可分解致癌芳香胺染料 (mg/kg) GB/T 17592-2011		符合
≤20	未检出	
本方法的检出限为 5mg/kg, 低于检出限的结果为“未检出”。		
耐水色牢度 (级) GB/T 5713-2013		符合
变色	≥3-4	4-5
沾色		
醋纤	≥3-4	4-5
棉	≥3-4	4-5
锦纶	≥3-4	4
聚酯纤维	≥3-4	4-5
腈纶	≥3-4	4-5
羊毛	≥3-4	4-5
耐酸汗渍色牢度 (级) GB/T 3922-2013		符合
变色	≥3-4	4-5
沾色		
醋纤	≥3-4	4-5
棉	≥3-4	4-5
锦纶	≥3-4	4-5
聚酯纤维	≥3-4	4-5
腈纶	≥3-4	4-5
羊毛	≥3-4	4-5
耐碱汗渍色牢度 (级) GB/T 3922-2013		符合
变色	≥3-4	4-5
沾色		
醋纤	≥3-4	4-5
棉	≥3-4	4-5
锦纶	≥3-4	4-5
聚酯纤维	≥3-4	4-5
腈纶	≥3-4	4-5
羊毛	≥3-4	4-5



报告编号(No.): GA23000831-1



第 3 页 共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
耐干摩擦色牢度(级) GB/T 3920-2008 沾色	≥3-4	4-5	符合
耐湿摩擦色牢度(级) GB/T 3920-2008 沾色	≥2-3	4-5	符合
耐皂洗色牢度(级) GB/T 3921-2008 变色 沾色	≥3-4	4-5	符合
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	3-4	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
A(1): 温度 40℃, 时间 30min, 钢球 0 颗			
耐光色牢度(级) GB/T 8427-2019 方法 3 变色(深色)	≥4	>4	符合
一阶段/对于深浅条的面料, 按蓝色羊毛标样 4 级进行曝晒, 深色按蓝色羊毛标样 4 级评级, 浅色按蓝色羊毛标 3 级评级。			
耐光、汗复合色牢度(碱汗)(级) GB/T 14576-2009 变色	≥3-4	4-5	符合
水洗尺寸变化率(%) GB/T 8628-2013、GB/T 8629-2017、GB/T 8630-2013 直向	-5.0~+2.0	-1.3	符合
干燥方式: 悬挂晾干/洗涤方式: 4N			
起球(级) GB/T 4802.1-2008	≥3-4	4	符合
方法 E: 压力 780cN, 起毛 0 次, 起球 600 次/具有特殊结构的织物加测反面			
顶破强力(N) GB/T 19976-2005	—	595	—
远红外性能(洗前) GB/T 30127-2013 远红外发射率	≥0.88	0.91	符合
远红外辐射温升(℃)	≥1.4	2.3	
远红外性能(洗涤 10 后) GB/T 30127-2013 远红外发射率	≥0.88	0.91	符合
远红外辐射温升(℃)	≥1.4	2.5	
洗涤程序: 7A×10; 干燥方式: 悬挂晾干			

以下空白

