

报告编号(No.): AB22101041



第 1 页共 3 页

委托方
Applicant 探路者控股集团股份有限公司

生产方
Manufacture 福建省宏港纺织科技有限公司

客户认定
样品信息
Submitted Sample
Description

商标: 探路者
样品名称: 面料-针织布,
数量: 1,
描述: 19SS 藏蓝 藏蓝色针织物
产品等级: 合格品,
安全类别: B 类
声明款号: TAJJAL81007 TAJJAK91078
面料编号: G20SS1230;

检验类型
Test Type

委托检验

来样日期
Date Received

2022-05-05

签发时间
Date Issued

2022-05-07

判定依据
Performance
Standard

GB 18401-2010 国家纺织产品基本安全技术规范
GB/T 22849-2014 针织 T 恤衫
Q/CPTLZ 0014.3-2017 TIEF DRY 功能性纺织品材料
T/FM 002-2020 针织面料理化性能要求



批准 Approved by

Wang Baojun (Director)

(检验检测专用章)
Stamp

备注
Notes

委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.
除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer.
*暂未申请认可。*The test isn't requested for confirmation temporarily.

报告编号(No.): AB22101041



第 2 页共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
纤维含量(%) FZ/T 01057-2007 GB/T 38015-2019			符合
	锦纶 81	锦纶 82.2	
	氨纶 19	氨纶 17.8	
pH 值 GB/T 7573-2009			符合
	4.0~8.5	6.4	
pH 值萃取介质为氯化钾溶液。			
甲醛含量(mg/kg) GB/T 2912.1-2009			符合
	≤75	未检出	
甲醛含量的检出限为 20mg/kg, 低于检出限结果为“未检出”。			
可分解致癌芳香胺染料(24种)(mg/kg) GB/T 17592-2011 GB/T 23344-2009			符合
	≤20	未检出	
可分解芳香胺染料的检出限为 5mg/kg, 低于检出限的结果为“未检出”。			
异味 GB 18401-2010 条款 6.7			符合
	无	无异味	
耐水色牢度(级) GB/T 5713-2013			符合
变色	≥3-4	4-5	
沾色			
羊毛	≥3-4	4-5	
腈纶	≥3-4	4-5	
涤纶	≥3-4	4-5	
锦纶	≥3-4	4-5	
棉	≥3-4	4-5	
醋酸	≥3-4	4-5	
耐汗渍色牢度(级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			
羊毛	≥3-4	4-5	
腈纶	≥3-4	4-5	
涤纶	≥3-4	4-5	
锦纶	≥3-4	4-5	
棉	≥3-4	4-5	
醋酸	≥3-4	4-5	
耐干摩擦色牢度(级) GB/T 3920-2008			符合
	≥3-4	4-5	

报告编号(No.): AB22101041



第 3 页共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
耐湿摩擦色牢度(级) GB/T 3920-2008			符合
	≥2-3	4-5	
耐皂洗色牢度(级) GB/T 3921-2008 A(1)			符合
变色	≥3-4	4-5	
沾色			
棉	≥3-4	4-5	
羊毛	≥3-4	4-5	
腈纶	≥3-4	4-5	
涤纶	≥3-4	4	
锦纶	≥3-4	4	
醋酯	≥3-4	4-5	
耐光色牢度(级) GB/T 8427-2008 方法 3			符合
	≥4	>4	
一阶段			
耐光、汗复合色牢度(碱性)(级) GB/T 14576-2009			符合
	≥3-4	4-5	
起毛起球(级) GB/T 4802.1-2008			符合
	≥3-4	4-5	
参数 E: 压力 780cN, 起球次数: 600 次			
蒸发速率-洗前(g/h) Q/CPTLZ 0014.3-2017 附录 C*			符合
	≥0.18	0.40	
蒸发速率-洗 5 次后(g/h) Q/CPTLZ 0014.3-2017 附录 C*			符合
	≥0.18	0.36	
洗涤方法: 按 GB/T8629-2017 中 A 型洗衣机 4N 程序连续洗涤 5 次, 再第一次洗涤前加入 (20.0±1.0) 克符合 GB/T8629-2017 中 6.1.3 规定的无磷 ECE 标准洗涤剂。洗涤程序结束后, 按照 GB/T8629-2017 中的 10.2.2 的烘干方法, 在 (60±5) °C 条件下烘干。			
透湿率-洗前(g/(m² · 24h)) GB/T 12704.1-2009			符合
	≥10000	12490	
透湿率-洗 5 次后(g/(m² · 24h)) GB/T 12704.1-2009			符合
	≥10000	12420	
洗涤方法: 按 GB/T8629-2017 中规定的 A 型洗衣机 4N 程序连续洗涤 5 次, 干燥方式采用程序 A。			

以下空白