

报告编号(No.): AB22011981



第 1 页共 3 页

委托方
Applicant 探路者控股集团股份有限公司

生产方
Manufacture 青岛金缕服饰有限公司

客户认定
样品信息
Submitted Sample Description
商标: 探路者
样品名称: 面料-菠萝布,
数量: 1,
描述: 冷灰紫色针织物,
产品等级: 合格品,
安全类别: B 类
声明款号: TAEEAK92274

检验类型 Test Type	委托检验	来样日期 Date Received	2022-05-12	签发时间 Date Issued	2022-05-17
-------------------	------	-----------------------	------------	---------------------	------------

判定依据 Performance Standard	GB 18401-2010 国家纺织产品基本安全技术规范 T/FM 002-2020 针织面料理化性能要求
------------------------------	--



批准 Approved by

Wang Baojun (Director)

(检验检测专用章)
Stamp

备注
Notes

委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.
除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer.
*暂未申请认可。*The test isn't requested for confirmation temporarily.

报告编号(No.): AB22011981



第 2 页共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
纤维含量 (%) FZ/T 01057-2007,GB/T 2910.24-2009	—	聚酯纤维 100	—
pH 值 GB/T 7573-2009	4.0~8.5	6.3	符合
pH 值萃取介质为氯化钾溶液。			
甲醛含量 (mg/kg) GB/T 2912.1-2009	≤75	未检出	符合
本方法的测定低限为 20mg/kg, 低于测定低限结果为“未检出”。			
异味 GB 18401-2010 条款 6.7	无	无异味	符合
可分解致癌芳香胺染料 (mg/kg) GB/T 17592-2011	≤20	未检出	符合
本方法的检出限为 5mg/kg, 低于检出限的结果为“未检出”。			
耐水色牢度 (级) GB/T 5713-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐酸汗渍色牢度 (级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐碱汗渍色牢度 (级) GB/T 3922-2013			符合
变色	≥3-4	4-5	
沾色			



报告编号(No.): AB22011981



第 3 页共 3 页

	标准(称)值 Requirement	实测值 Results	单项判定 Judgement
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐干摩擦色牢度(级) GB/T 3920-2008			符合
沾色	≥3-4	4-5	
耐湿摩擦色牢度(级) GB/T 3920-2008			符合
沾色	≥2-3	4-5	
耐皂洗色牢度(级) GB/T 3921-2008			符合
变色	≥3-4	4-5	
沾色			
醋纤	≥3-4	4-5	
棉	≥3-4	4-5	
锦纶	≥3-4	4-5	
聚酯纤维	≥3-4	4-5	
腈纶	≥3-4	4-5	
羊毛	≥3-4	4-5	
耐光色牢度(级) GB/T 8427-2019 方法 3			符合
变色(深色)	≥4	>4	
耐光、汗复合色牢度(碱汗)(级) GB/T 14576-2009			符合
变色	≥3-4	4-5	
顶破强力(N) GB/T 19976-2005			符合
	≥250	1090	

以下空白