

报告编号(No.): GS22000667-1



第 1 页共 3 页

委托方
Applicant 探路者控股集团股份有限公司

生产方
Manufacture 青岛金缕服饰有限公司

客户认定
样品信息
Submitted Sample Description
商标: 探路者
样品名称: 320D 涤纶塔斯隆,
数量: 1,
描述: 灰绿色机织物
产品等级: 合格品,
安全类别: B 类
声明款号: TAEEAK91565

检验类型 Test Type	委托检验	来样日期 Date Received	2022-05-30	签发时间 Date Issued	2022-06-06
-------------------	------	-----------------------	------------	---------------------	------------

判定依据
Performance Standard
FZ/T 81007-2012 单、夹服装
GB 18401-2010 国家纺织产品基本安全技术规范
GB/T 4744-2013 纺织品 防水性能的检测和评价 静水压法
GB/T 4745-2012 纺织品 防水性能的检测和评价 沾水法



批准 Approved by

Wang Baojun (Director)

(检验检测专用章)
Stamp

备注
Notes

委托检验仅对来样负责, 不承担其他连带责任。This report is valid only for the samples delivered by clients.
对检验报告若有异议, 应于收到报告之日起 15 日内向检验单位提出, 逾期不再受理。If there is any objection concerning the report, it is required that the objection should be put forth to the center within 15 days from the reception date of the report.
除非客户要求, 本报告检测结果及符合性判定不考虑测量结果的不确定度。Measurement uncertainty is not considered on the results and conformity assessment in the report unless required by the customer.
*暂未申请认可。*The test isn't requested for confirmation temporarily.
样品及数据采用 AB22103132-1

报告编号(No.): GS22000667-1



第 2 页共 3 页

	标准 (称) 值 Requirement	实测值 Results	单项判定 Judgement
纤维含量(%) FZ/T 01057-2007 GB/T 2910.24-2009			符合
	聚酯纤维 100 —	聚酯纤维 100 -涂层除外	
pH 值 GB/T 7573-2009			符合
	4.0~8.5	6.3	
pH 值萃取介质为氯化钾溶液。			
甲醛含量(mg/kg) GB/T 2912.1-2009			符合
	≤75	未检出	
甲醛含量的检出限为 20mg/kg, 低于检出限结果为“未检出”。			
可分解致癌芳香胺染料 (24 种) (mg/kg) GB/T 17592-2011 GB/T 23344-2009			符合
	≤20	未检出	
可分解芳香胺染料的检出限为 5mg/kg, 低于检出限的结果为“未检出”。			
面料耐水色牢度(级) GB/T 5713-2013			符合
变色	≥3	4-5	
沾色			
羊毛	≥3	4-5	
腈纶	≥3	4-5	
涤纶	≥3	4-5	
锦纶	≥3	4-5	
棉	≥3	4-5	
醋酯	≥3	4-5	
面料耐汗渍色牢度(级) GB/T 3922-2013			符合
变色	≥3	4-5	
沾色			
羊毛	≥3	4-5	
腈纶	≥3	4-5	
涤纶	≥3	4-5	
锦纶	≥3	4-5	
棉	≥3	4-5	
醋纤	≥3	4-5	
面料耐干摩擦色牢度(级) GB/T 3920-2008			符合
	≥3	4-5	
面料耐湿摩擦色牢度(级) GB/T 3920-2008			符合
	≥2	4-5	

报告编号(No.): GS22000667-1



第 3 页共 3 页

	标准（称）值 Requirement	实测值 Results	单项判定 Judgement
拒水性 GB/T 4745-2012			具有很好的抗沾湿性能
沾水等级(级)	4	4	
静水压值 P(kPa) GB/T 4744-2013			具有优异的抗静水压性能
	P≥50	>50	

以下空白